TÜVRheinland® CERT ISO 9001

PoudMet Metal Powders

Technical Data Sheet

Date Revision	Révision
31/10/2013	2

Material : Our / Reference

2328UAL **POUDMET Bronze powder** **25 GR 90/10-325**

Bronze powder, water atomised, irregular shape

Inspection Characteristic	Unit	Lower Limiting Value	Upper Limiting Value	Desired Value	Indicative Value	Méthode
Physical						
Physical analysis :						
Sieve analysis ISO 4497 cumulative :						
> 63 µm	%		0,10			IN.V.1007
> 45 µm	%		5,00			IN.V.1007
> 40 µm	%		10,00			IN.V.1007
Average particle size Fisher dF	µm					IN.V.1011
Specific surface Fisher	cm²/g					IN.V.1011
Apparent density ISO 3923/1 - 2,5 mm	g/cm3	2,90	3,50			IN.V.1010
Chemical						
Chemical analysis :						
Tin (Sn)	%	9,00000	10,50000			IN.V.1138
Others	%		0,50000			IN.V.1138
Hydrogen Loss ISO 4491/2	%		0,200			IN.V.1134

FDS : 25GR

All statements, technical information and recommendations herein are based on tests and data which our Company believes to be currently reliable. The accuracy or completeness thereof is not guaranted and no warranty of any kind is made with respect thereto. Product characteristics may change due to technical development and / or improvment of production methods.

Adresse postale
Poudmet S.A.S.
BP 90319
F 60332 LIANCOURT CEDEX

Tél. : + 33 (0) 3 44 69 12 31
Fax : + 33 (0) 3 44 69 12 30
E-mail :info.poudmet@poudmet.fr

S.A.S. au capital de 500.000 €
SIRET Beauvais 528 945 660 000 25
TVA FR24 528 945 660
RCS Paris 528 945 660
APE 2444 Z