



Management
System
ISO 9001:2015

www.tuv.com
ID 910506865

Technical Data Sheet

Date Revision
08/01/2008

Révision
5

Material : Our / Reference

1838

Iron carbonyl powder

430T EN

Iron powder, mechanically hard, spherical shape

Inspection Characteristic	Unit	Lower Limiting Value	Upper Limiting Value	Desired Value	Indicative Value	Méthode
Physical						
Physical analysis :						
Laser granulometry :						
Particle size D 50 %	µm	3,90	5,20			
Chemical						
Chemical analysis :						
Iron (Fe)	%	97,50000				
Total carbon (C)	%		0,90000			
Nitrogen (N)	%		1,000			
Oxygen (O2) ISO 4491/4	%		0,60000			

FDS :

All statements, technical information and recommendations herein are based on tests and data which our Company believes to be currently reliable. The accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto. Product characteristics may change due to technical development and / or improvement of production methods.

Adresse postale
Poudmet S.A.S.
26, rue du moulin
F 60140 BAILLEVAL

Tél. : + 33 (0) 3 44 69 12 31
Fax : + 33 (0) 3 44 69 12 30
E-mail : info.poudmet@poudmet.fr

S.A.S. au capital de 500.000 €
SIRET Beauvais 528 945 660 000 25
TVA FR24 528 945 660
RCS Paris 528 945 660
APE 2444 Z